



MSM-228

Threaded Magnet M8




Data

Housing Material	PA 6.6
Potting Material	Epoxy, black
Orientation	axially

Magnetic Material	N35H	
Remanence Br	mT	1190
Coercivity HcB	kA/m	828
Coercivity HcJ	kA/m	1274
Energy Product (BH) max.	kJ/m ³	275
Magnetic Moment M	x10 ⁻⁵ Vs cm	1.50
Operating Temperature	°C	-20 to 85
Temperature Coefficient Tk(Br)	%/°C	-0.12

Nominal values unless otherwise specified

Dimensions in mm



Customized types, other magnet materials and high temperature grades available.